



# SMC 0125

## SMC Low Shrink Polyester

### Technical Data Sheet

Update: June 2019

### Description :

0125 is a pigmented LS SMC reinforced with chopped glass fibres (50% 25mm + 50% 50mm) designed for gas box application.

0125 is grey pigmented with good fire, electrical and ageing performances.

### Moulding features (\*):

	Unit		Test method
Reactivity			ISO 12114
• Moulding T°C :	°C	145	
• Thickness :	mm	3,2	
• Cure time :	s	29	
Density		1.85	ISO 1183
Shrinkage	%	0,08	NF EN 1842

(\*) Compression moulding without flow

### Use recommendations :

High temperature from 145°C to 150°C under high pressure around 80 bars

### Application :

Gas box

### COMPOSITION

Product nature	Unit	Ratio
Glass fibres content	%	20
Resins content	%	27.1
Fillers content	%	51.2
Other products content	%	1.7

Remark: contains TiO<sub>2</sub>; use chromated tool is recommended

### APPEARANCE

	Unit	
Rolls :	kg	1270
SMC width :	cm	148
Material support :	-	COEX
Surface weighth :	kg/m <sup>2</sup>	6.25
Colour		GREY RAL 7035 AFNOR

### MECHANICAL PROPERTIES WITHOUT FLOW AT 23 °C

#### Moulding conditions

Temperature	°C	145
Thickness	mm	3.1
Curing time	sec	44
Covering	%	100
Part size	mm	250X120
Layers		1

	Unit		Test method
Flexural test (*)			ISO 178
- Breaking stress	MPa	135	
- Elastic modulus	MPa	9000	
- Deviation at break	mm	3.8	
Impact test (Charpy)(**)	kJ/m <sup>2</sup>	52	ISO 179
Tensile test (***)			ISO 527
- Breaking stress	MPa	45	
- Elastic modulus	MPa	10000	
- Elongation at break	%	1,4	

(\*) Average on first industrial productions

(\*\*) Average on first industrial productions

(\*\*\*) Average on first industrial productions

### MECHANICAL PROPERTIES WITH FLOW AT 23 °C

#### Moulding conditions

Temperature	°C	145/150
Thickness	mm	3,8
Curing time	sec	44
Covering	%	38
Part size	mm	700X300
Layers		3

	Unit	Perp/Para	Test method
Flexural test(*)			ISO 178
- Breaking stress	MPa	100/150	
- Elastic modulus	MPa	9500/10500	
- Deviation at break	mm	3.6/3.8	
Tensile test (**)			ISO 527
- Breaking stress	MPa	37/63	
- Elastic modulus	MPa	10500/11500	
- Elongation at break	%	0.9 /1.1	

(\*) Average on the first industrial production

(\*\*) Average on the first industrial production


#### Mixt Composites Recyclables

ZI les îles Féray – BP 94 07302 Tournon-sur-Rhône  
Tel. : +33 4 75 07 18 18 - Fax : +33 4 75 07 11 77

## OTHER PROPERTIES

	<i>Unit</i>		<i>Test method</i>
Oxygen limit index	%	>23	ISO 4589-2
Incandescent filament 960°C	s	<15	NFC 20455
Combustion speed		FH1	ISO 1210
Electrical resistance	V	600	NFC 26220

**Reactivity :**  
**The reactivity datas below are given as**  
**a technical information.**



**Mixt Composites Recyclables**  
 ZI les îles Féray – BP 94 07302 Tournon-sur-Rhône  
 Tel. : +33 4 75 07 18 18 - Fax : +33 4 75 07 11 77